

		Ventec VT-4B3 Al 5052				Ventec VT-4B5 5052				Ventec VT-4B5 (copper)					
		Tg [°C]	Die	Th. conductivity	Core	Tg [°C]	Die	Th. conductivity	Core	Tg [°C]	Die	Th. conductivity	Core		
		135	50 μm	3 W / m.K	Al 5052	120	50 μm	4,2 W / m.K	Al 5052	120	50 μm	4,2 W / m.K	Copper		
		<a href="#">datasheet</a>				<a href="#">datasheet</a>				<a href="#">datasheet</a>					
Tloušťka materiálu (μm)	Tloušťka Cu (μm)					Tloušťka Cu (μm)					Tloušťka Cu (μm)				
	00/18	00/35	00/70	00/105	00/140	00/18	00/35	00/70	00/105	00/140	00/18	00/35	00/70	00/105	00/140
1000	○	✓	✓	○	○	○	✓	✓	○	○	○	○	✓	○	○
1500	○	✓	✓	○	○	○	✓	✓	○	○	○	○	○	○	○
3000	○	○	○	○	✓	○	○	○	○	○	○	○	○	○	○

		Polytherm TC-Lam Cu 2.0				Polytherm TC-Lam 1,3				
		Tg [°C]	Die	Th. conductivity	Core	Tg [°C]	Die	Th. conductivity	Core	
		100	100 μm	2 W / m.K	Copper	100	100 μm	1,3 W / m.K	Al 5052	
		<a href="#">datasheet</a>				<a href="#">datasheet</a>				
Tloušťka materiálu (μm)	Tloušťka Cu (μm)					Tloušťka Cu (μm)				
	00/18	00/35	00/70	00/105	00/140	00/18	00/35	00/70	00/105	00/140
1000	○	○	✓	○	○	○	○	✓	○	○
1500	○	○	○	○	○	○	✓	✓	○	○

✓ skladem ○ na objednání